

# Technical Data Sheet

## Multicor LH 3 Plus

---

### Product description

- anti-corrosion oil
- on the basis of a low-odour solvent which is free of aromatics

### Characteristics

Colour / Appearance:	brownish, unclear
Density/15°C / DIN 51 757:	820 kg/m <sup>3</sup>
Flash point (Pensky-Martens) / DIN EN ISO 2719:	> 61 °C
Type of protective film:	waxy, touch-dry
Colour of the protective film:	transparent, slightly yellowish
Film thickness after dipping:	approx. 20 µ
Kesternich test / DIN EN ISO 6270-2:	> 40 cycles
Salt spray test / DIN EN ISO 9227:	> 100 hours

### Application

**Multicor LH 3 Plus** is used as long-term preservative agent e.g. for machines which are exposed to all weather conditions during the whole year as well as for the external preservation of parts and systems. With an adequate packaging the product is also suitable for maritime climate.

The product is applied in as-delivered condition, outdoors or in well-ventilated rooms by dipping, spraying or manually e.g. by brush.

**IMPORTANT: Stir well before taking out!**

### Degreasing

We recommend degreasing with solvent cleaners.

05411

09/2013-05411-5

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can not be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.

1 / 2

# Technical Data Sheet

## Multicor LH 3 Plus

---

### Storage

As the product is thickening at lower temperatures, we recommend to store it at room temperature (approx. 20 °C). However, this is a reversible process.

### Note / Attention

The specifications of the film thickness are only guiding values which are highly dependent on the surface texture and the type of applications.

05411

09/2013-05411-5

The statements made in this publication are according to our present knowledge. They do not absolve the user from own examinations. A legally binding assurance of certain properties or suitability for a specific use can not be derived from our statements. Possibly existing laws and regulations concerning the handling and use of our products have to be observed by the receiver of our products himself.

2 / 2